

Material Data Sheet Guide Tape TB

PTFE-BR40 T110 - brown

General

T110-BR40 is a PTFE (Polytetrafluorethylene) filled with 40% bronze in brown color. The fillers make the material more resistant to “cold flow” and provide the necessary properties to use it as composite seals with energizer to withstand high pressures. It has similar chemical resistance and can be used in the same temperature range like virgin PTFE what makes it a very universal seal material. T110-BR40 should not be used for dynamic applications in water.

Physical properties

Density:	DIN 53479	g/cm ³	3,05 – 3,12
Hardness:	DIN 53505	Shore D	62 - 67
Tensile strength:	DIN 53455	N/mm ²	23 - 28
Elongation at break:	DIN 53455	%	200 - 250
Ball Hardness H132/6:	DIN 53456	N/mm ²	36
Coefficient of friction (dyn.):	ASTM D1894	μ	0,13
Wear factor (K):	ASTM D3702	cm ³ min10 ⁻⁸ /kg m h	9 - 13
Compr. strength at 1% deformation:	DIN 53454	N/mm ²	7 - 9
Therm. Exp. Coeff. (lin.) 25-100°:	DIN 53328	10 ⁻⁵ /°C	10 - 11,5
Min. service temperature:		°C	- 200
Max. service temperature:		°C	260

Chemical resistance

Water up to 70°	R	Vegetable oils	R
Water up to 90°	R	Fuels	R
HFA	R	Ozone	R
HFB	R		
HFC	R	Air up to 100°	R
HFD	R	Air up to 150°	R
Mineral oils	R	Air up to 200°	R

Key to chemical resistance: **R = resistant** **S = suitable** **U = unsuitable**

Main application

Guide rings, bushings, housings, high precision parts.

Analysis and Evaluation

The properties relate to fundamental values of PTFE. Product values mentioned above are corresponding to ASTM or DIN standards and have been tested on standardized plates in the laboratory.